

Quantum Phase Fluctuation in High T_c Superconductors

B.K.CHAKRAVERTY

LEPES/CNRS, BP166, 25 Av. des Martyrs, F-38042 Grenoble Cedex 9

(July 1st, 1999)

Abstract

If phase coherence determines the superconducting transition temperature T_c in the cuprate oxides, it is of great interest to understand the role that dynamics of the phase fluctuation plays in bringing about depletion of the superconducting condensate. We will show that a phase correlation function can be calculated that allows us to describe depletion of superconducting condensate as a result of the quantum fluctuation. In two dimension, dynamic phase fluctuation or pair fluctuation gives rise to a condensate depletion linear with temperature as $T \rightarrow 0$ in superconductors with nodes at the fermi surface.

Superconducting order parameter has an amplitude and a phase. In the ground state the phase has to be blocked in all space. It has been suggested [1] that the superconducting transition temperature T_c in the oxide materials is related to the loss of long range phase coherence. Beyond T_c the system lives, in this model, unlike classical superconductors in an ill understood mixture of Cooper pairs that have a nonzero amplitude and a highly fluctuating phase. The dynamics of the phase fluctuation and depletion of superfluid density of the superconducting state is the object of this study.

We write the superconducting order parameter as $\psi(t)$.where

$$\psi(t) = |\psi| \exp(i\theta(x,t)) \quad (1)$$

where $|\psi|$ is the amplitude assumed constant in space and $\theta(x,t)$ is the phase assumed

fluctuating in space and time..The phase dynamics is contained in the simple hydrodynamic phase fluctuation hamiltonian [2]

$$H = \frac{1}{2}\kappa_s (\nabla\theta)^2 + \frac{1}{2\chi_\rho} (\partial\rho_s)^2 + \frac{1}{2}\partial\rho_s e^* \phi(t) \quad (2)$$

Here κ_s is the superfluid phase stiffness and χ_ρ is the density susceptibility related to the density of states of paired electrons, $\partial\rho_s$, a local density fluctuation that has long range coulomb interaction with nonlocal potential $\phi(t)$ and e^* is the pair charge. We note that θ and the pair density ρ_s are conjugate quantities so that all the dynamics of θ is contained in the excess pair charge $e^* \partial\rho_s$, the subscript s meaning superconducting phase. We have the Josephson relation governing the dynamics of the phase to induced local potential $\phi(t)$ through

$$\begin{aligned} \frac{\partial\theta}{\partial t} &= \frac{e^*}{\hbar} \phi(t) \\ \nabla^2 \phi &= e (2\partial\rho_s - \rho_{qp}) \end{aligned} \quad (3)$$

Here ρ_{qp} is local quasiparticle population, if there is any . Let us assume that the coulomb interaction given by the third term of the hamiltonian (2) is zero. The resulting hamiltonian can be written as

$$H_o = \int dV \left(\frac{\rho_o \nu_s^2}{2} + \frac{c_o^2 (\partial\rho_s)^2}{2\rho_o} \right) \quad (4)$$

where ρ_o is the condensate mass density, ν_s is the superfluid flow, proportional to $\nabla\theta(x,t)$ and c_o is the bare fermi velocity. The hamiltonian gives the elementary phase excitation as the Boguylubov-Anderson mode with the well-known dispersion $w_q = cq$ where is $c = \frac{c_o}{\sqrt{2}}$, in 2d . In order to obtain the depletion of superfluid density due to dynamic phase fluctuation we use the usual trick of adding to the phase hamiltonian (4) an amplitude modulation term that represents an infinitesimal coupling to the medium , a source term

$$H' = -\frac{1}{2}\eta \sum_x (\psi + \psi^*) \quad (5)$$

Where η is the interaction between pairs and the medium which in the end will be allowed to go to zero . The fluctuation of the longitudinal part of the order paramter is defined through

$$\begin{aligned}\Delta'(x) &= \Delta - \Delta_o \\ \Delta &= \psi + \psi^*; \Delta_o = \psi_o + \psi_o^* \\ \Delta' &= -\sqrt{\frac{n_o}{\Omega}} \sum_q \theta_q^2\end{aligned}\tag{6}$$

Here n_o is the condensate density ($n_o \sim \frac{N_h}{2}$ where N_h is the hole density in oxide materials), Ω is an atomic volume in 3d (in 2dimension n_o is the pair density per unit area while Ω is the area of an unit cell on the surface), θ_q is the fourier transform of the phase fluctuation θ . The total fluctuation hamiltonian reads

$$H = H_o + H'\tag{7}$$

This can be transformed in the fourier space as

$$H(\eta) = \sum_q \left[\frac{n_o q^2}{2m^2} |\theta_q|^2 + \frac{mc_o^2}{2n_o} |\rho_q|^2 + \frac{\eta}{2} \sqrt{\frac{n_o}{\Omega}} |\theta_q|^2 \right]\tag{8}$$

The excitation spectra of the phase mode is significantly modified, due to coupling η and is given by (after restoring $\hbar$)

$$\varpi_q(\eta) = \hbar c q \left(1 + \frac{\eta m}{\hbar^2 n_o q^2} \sqrt{\frac{n_o}{\Omega}} \right)^{\frac{1}{2}}\tag{9}$$

At small momenta we now have a gap in the excitation spectra given by

$$\varpi_o(\eta) = c \left[\frac{\eta m}{n_o} \sqrt{\frac{n_o}{\Omega}} \right]^{\frac{1}{2}}\tag{10}$$

It is relatively straightforward to derive the relation for the condensate density $n_o(T)$ at low temperature due to phase fluctuation. By writing the grand canonical hamiltonian

$$\hat{H} = H - \mu N\tag{11}$$

we can show that [3]

$$\langle \psi \rangle = \sqrt{n_o(T) \Omega} = - \left\langle \frac{\partial \hat{H}}{\partial \eta} \right\rangle_{\eta=o} = - \left| \frac{\partial G(\eta)}{\partial \eta} \right|_{\eta=o} \quad (12)$$

Here G is the Gibb's free energy and is given by

$$G(\eta, T) = G(\eta, o) + \frac{kT\Omega}{(2\pi)} \int q dq \ln [1 - \exp -\beta \varpi_q(\eta)] \quad (13)$$

This allows us to write in two dimension

$$n_o(T) = n_o - \frac{\sqrt{n_o \Omega}}{\pi} \int_q q dq N_q^o \left[\frac{\partial \varpi_q(\eta)}{\partial \eta} \right]_{\eta=o} \quad (14)$$

Here N_q^o is the bose factor for the unperturbed energy given by

$$N_q^o = \frac{1}{\exp\left(\frac{\hbar c q}{kT}\right) - 1} \quad (15)$$

Using equation (9) and substituting it into equation (14), we obtain integrating equation (14) as $T \rightarrow 0$, the condensate density in two dimension

$$\frac{n_o(T) - n_o}{n_o} = -\frac{1}{2\pi} \frac{mkT}{n_o \hbar^2} \simeq -\frac{1}{\pi} \frac{mkT}{N_h \hbar^2} \quad (16)$$

In this expression m is the electronic mass and N_h is the total hole density. Care has to be exercised in using the expression (16) as n_o , the pair density at $T=0$ may be considerably less than $N_h/2$ due to quantum fluctuation which we calculate in the next section. In three dimension the same calculation gives a T^2 diminution of the condensate fraction as $T \rightarrow 0$.

The quantum phase fluctuation will be studied with an lattice hamiltonian equivalent to that of expression (4) that we have used earlier [4]. We have pointed out that almost all high T_c cuprates are characterised universally as domains of coherence length ξ separated by about the same distance from neighboring domains and that phase coherence between the domains is assured by condensate pair transfer between them at a rate given by the Josephson coupling energy J . This gives the discrete or coarse-grained version of the hamiltonian of (4) as a Josephson lattice hamiltonian

$$H_\theta = -J \sum_{ij} (\cos(\theta_i - \theta_j)) + \frac{(\partial \rho_s)^2}{2\chi_\rho} \quad (17)$$

The energy increase for a single cooper pair charge $\partial\rho_s = \pm 2e$ is given by in this pure transfer process

$$\epsilon_c = \frac{(\partial\rho_s)^2}{2\chi_\rho} = \frac{2e^2}{\chi_\rho} \quad (18)$$

ϵ_c is the quantum unit of energy increase for a single cooper pair transfer. At $T = 0$, the lattice hamiltonian is equivalent to a $d + 1$ system and is given exactly by

$$H_\theta^{d+1} = \frac{1}{g} \sum_{ij} \cos(\theta_i - \theta_j) \quad (19)$$

where a quantum coupling constant for quantum fluctuation can be defined given by

$$g = \sqrt{\frac{\epsilon_c}{J}} \quad (20)$$

We have shown [4] that beyond a critical coupling constant $g = g_c$, quantum fluctuation destroys the superconducting ground state and drives the system insulating. We will derive a similar characteristic from the phase correlation function below.

We define the phase correlation function at a point x by

$$\Phi_x = \langle \exp[i\theta(t) - i\theta(0)] \rangle \quad (21)$$

Since phase and charge are conjugate variables, the charge operator ρ induces transition from the ground state $\langle \Psi_G |$ to an excited state $\langle \Psi_E |$ with a probability given by the matrix element $|\langle \Psi_E | \rho | \Psi_G \rangle|^2$ such that we have the sum rule

$$\sum_E (E - E_G) |\langle \Psi_E | \rho | \Psi_G \rangle|^2 = \epsilon_c \quad (22)$$

The phase correlator can be written as

$$\left\langle \exp -i \frac{(E - E_g) t}{\hbar} \right\rangle = \Phi_x \quad (23)$$

We will now calculate the phase correlator Φ using the lattice hamiltonian (16). Considering θ as an operator we write the commutator of $\theta(0)$ and $\theta(t)$

$$[\theta(0), \theta(t)] = \frac{i\hbar}{\chi_\rho} \sin \varpi_o t \quad (24)$$

where ϖ_o is a characteristic frequency of the phase mode. We now use the operator identity

$$\exp(A + B) = e^A e^B e^{-\frac{[A, B]}{2}}$$

to obtain

$$\begin{aligned} & \exp i\theta(0) \exp -i\theta(t) \\ &= \exp i[\theta(0) - \theta(t)] \exp \left(\frac{i\epsilon_c}{\hbar\varpi_o} \sin \varpi_o t \right) \end{aligned} \quad (25)$$

we note that at small time $\theta(t) \approx \theta(0)$ and the correlator behaves like $\exp(i\frac{\epsilon_c t}{\hbar})$ as it should.

This expression can be fed back into (23) to get after a little algebra

$$\left\langle \exp -i \frac{(E - E_g) t}{\hbar} \right\rangle = \Phi_x = \sum_{n=-\infty}^{n=+\infty} P(n\hbar\varpi_o) \exp -in\varpi_o t \quad (26)$$

The fourier transform $P(n\hbar\varpi_o)$ gives the probability that n quanta of phase oscillation mode ϖ_o will be excited in the medium. This is explicitly written in terms of the Bessel functions I_n

$$P(n\hbar\varpi_o) = \exp -\langle \theta^2 \rangle \mathbf{I}_n \left(\frac{\epsilon_c}{\hbar\varpi_o \sinh \left(\frac{\hbar\varpi_o \beta}{2} \right)} \right) \exp -\left(\frac{n\hbar\beta\varpi_o}{2} \right) \quad (27)$$

Here $\exp -\langle \theta^2 \rangle$ is like the Debye-waller factor and is given by the ratio of two characteristic enegies of the problem

$$\langle \theta^2 \rangle = \frac{\epsilon_c}{\hbar\varpi_o} = g \quad (28)$$

where a quantum coupling constant has been defined which tells us how many quanta will be excited during a typical pair transfer so as to cause dephasing and depletion of the superconducting condensate. The expression for **P(0)** gives us the probability of **condensate fraction at a given T.**

This allows us to write for the spectral density at T=0 as

$$A(\omega) = (\exp -g) \left(\sum_{n=0}^{n=\infty} \frac{g^n}{n!} \delta(\omega - \epsilon_c - n\varpi_o) \right) \quad (29)$$

.The spectral density obey the following sum rules

$$\int_o^\infty \omega A(\omega) d\omega = \epsilon_c \quad (30)$$

$$\int_o^\infty \omega^m A(\omega) d\omega = \langle \omega^m \rangle \quad (31)$$

Expression(29) is plotted in figure 1 for a variety of values of g. The rapid depletion of spectral weight $A(\omega = o)$ i.e that of superfluid density at around $g=g_c$ is to be seen. The two quantum coupling constants of the expressions (28) and (20) are the same if we identify the characteristic energy ϖ_o with the average energy scale of the Josephson hamiltonian (19) as $\varpi_o = \sqrt{\epsilon_c J}$; ϖ_o is just then a debye energy or a characteristic pair fluctuation frequency. We notice from the figures how the spectral weight goes from a poisson distribution to a gaussian as the coupling constant increases. The gaussian spectral distribution indicates that the ground state is coupled to a bath of continuum of excitations. We also note that the spread of the spectral weight as g increases does not mean we are in the excited state for we are still at T=0. If there were no interactions ($g=0$) we will get a single delta function at $\omega = \epsilon_c$. For $g \neq 0$ we are still in the ground state but the coupled system has n quanta of phase oscillation modes excited with a certain probability $P(n\hbar\varpi_o)$. The effective superfluid density at T=0 can be written as

$$\frac{n_o}{N_h} \sim \exp -g \quad (32)$$

We show in table 1 this fraction for a variety of optimum doped materials taken from [5]. In the table the effective number of holes per copper, n_{eff} has been measured by summing the oscillator strength $N_{eff}(\omega)$ upto a frequency of the order of charge transfer band ($\sim 12000 \text{ cm}^{-1}$). As temperature is reduced, the increase in area at low frequencies is compensated by a decrease in area at high frequencies. *However, below T_c , there is a loss of area, which must*

be coming mostly from the free carrier peak at $\omega \rightarrow 0$, as the authors conclude. The number of supeconducting carriers n_s is obtained in two ways: from the London penetration depth λ_L and from the Drude peak, in the normal state. The measured n_s values are almost same as the number of Drude carriers n_d (these later are not shown here). Thus only a quarter to a fifth of the total doping induced holes appear in the delta function ! A value of $g \approx 1$ can be taken indicating that even at optimum doping considerable quantum fluctuation is going on. It is interesting to compare this ratio of $\frac{n_{eff}}{n_s}$ with Ornstein et al's [5] optical data where a bulk plasma frequency from band structure value was estimated to be ~ 3.5 e.v compared to 1.4 e.v of the superfluid condensate at $\omega=0$ for YBa Cuo and which reflects faithfully the ratio observed in the table 1.

Table1

material	$T_c (K)$	$\frac{n_{eff}}{cu}$	$\frac{n_s}{cu}$	$\frac{n_s}{n_{eff}} \%$
La_2CuO_4	40	0.15	0.028	19
$BiPbSrCu_2O_8$	79	0.37	0.085	23
$BiSrCaCu_2O_8^c (a)$	85	0.44	0.100	23
$BiSrCaCu_2O_8^c (b)$	85	0.48	0.090	19
$YBa_2Cu_3O_7 (a)$	91	0.44	0.096	22
$YBa_2Cu_3O_7 (b)$	91	0.59	0.125	21
$Tl_2Ba_2CaCu_2O_8$	110	0.54	0.115	21

The underlying physics of quantum phase fluctuation is quite similar to the boson shake up process in the strong coupling polaron problem [6]

We are now in a position to calculate the temperature coefficient of depletion of superfluid density using expression(16) and (33) and renormalising the temperature T by $\tau = \frac{T}{T_c}$ so that we get the depletion coefficient in the dimensionless form as

$$\frac{\partial \left(\frac{n-n_o}{n_o} \right)}{\partial \tau} = - \frac{\exp(g) m k T_c}{\pi N_h \hbar^2} \quad (33)$$

Using for high T_c superconductors the following numbers $T_c = 100^\circ K$, $m = 5$ electron mass, $N_h \approx 10^{14}/cm^2$ and $g = 1$, we obtain the coefficient as ~ -0.56 in reasonable agreement with the values in the literature [7]. The ratio on the right hand side is mkT_c/n_s , which is really a constant as shown by Uemura's plot. A linear T decrease of superconducting condensate due to *static phase fluctuation* has been suggested in the past [8] and that has been recently contested [9]. There is also the theory of low energy quasi-particle excitation [10] at the d-wave gap nodes explaining the linear T-dependence but the numerical agreement seems to need considerable fermi-liquid correction [9] to fit the data.

The overall treatment in this paper has assumed perfect screening of charge fluctuation $\partial\rho_s$ in the condensate so that plasma mode is not excited. we can speculate that in d-wave superconductor this may well be so due to possibility of low energy quasiparticle excitation as a result of phase excitation. The latter shifts the quasiparticle energy due to doppler effect [11] of the local superfluid flow by an amount

$$\partial E_{qp} = \hbar \vec{k}_f \cdot \vec{v}_s$$

at the fermi surface i.e. at the nodal points. Here $\vec{v}_s = -(\hbar/2m)\nabla\theta$, is the local superfluid velocity. The quasiparticle population created due to this doppler shift is $\rho_{qp} \sim \int_0^{\partial E_{qp}} f(E) N(E) \partial E$ where $N(E)$, the quasiparticle density of states. The integral picks up significant weight only because of d-wave nodes, where the product $N(E)f(E)$ is $\neq 0$. The condition of perfect screening (local charge neutrality) $\rho_{qp} \approx \partial\rho_s$ may be easily satisfied so that long range coulomb interaction is suppressed. A background quasiparticle density of the order of 10% has been inferred from microwave measurements on high T_c oxides [12]. The local charge neutrality condition implies $\text{div } \vec{J}_s + \text{div } \vec{J}_{qp} = 0$, where $\vec{J}$'s are superconducting and quasiparticle currents respectively. For intense local phase gradient, the more stringent well-known criterion of total (although local), destruction of condensate, due to quasiparticle backflow current applies with $\vec{J}_s^{crit} = -\vec{J}_{qp}^{crit}$.

REFERENCES

- [1] B.K. Chakraverty, A. Taraphder, M. Avignon, Physica C235-240, 2323 (1994); V.J. Emery and S. Kivelson, Nature 374 , 434 (1995)
- [2] T.V. Ramakrishnan, Physica Scripta T27, 24 (1989); S. De Palo, C. Castellani, C. Di Castro and B.K. Chakraverty, cond-mat/9901305, accepted in Phys Rev B
- [3] John W.Negele and Henri Orland “Quantum many particle system” Addison Wesley (1988) p.108
- [4] B.K. Chakraverty and T.V. Ramakrishnan, Physica C 282, 290 (1997); S. Doniach, Phys Rev B24, 5063 (1981)
- [5] D.B. Tanner et al, Physica B 244, 1 (1998); Joseph Orenstein et al, Phys Rev B42, 6342 (1990)
- [6] J. Ranninger and A. Romano, Phys.Rev.Lett, 80(1998); S. Ciuchi, F. de Pasquale, S. Fratini and D. Feinberg, Phys.Rev.B 56, 4494 (1997)
- [7] W.N. Hardy et al, Phys.Rev.Lett. 70, 3999 (1993)
- [8] E.Roddick and D.Stroud, Phys. Rev. Lettr., 74, 1430 (1995)
- [9] A.J.Mills, S.M.Girvin, L.B.Ioffe and A.I.Larkin, Cond-mat:9709222
- [10] P.A.Lee and X.G.Wen, Phys.Rev.Lett. 78 , 4111 (1997)
- [11] P.G. de Gennes, “Superconductivity of Metals and Alloys” (Addison-wesley,N.Y.1992), p.144; M. Franz and A.J. Millis, Phys.Rev.B 58, 14572 (1998)
- [12] J.R. Waldram et al, Phys Rev B 55, 3222 (1997)Phys Rev B 55, 3222 (1997)(1997)

Figure 1: spectral density $A(\omega)$ as a function of phase quanta n . a) coupling constant $g = 1$; b) $g = 3$; c) $g = 8$.

